

Versatill® QP5 Designed Fluid

Description

Versatill® Designed Fluid is a family of proprietary blended fluids based on fluorinated (HFE-458) and chlorinated (t-DCE) carbons. Versatill® Designed Fluid covers a large spectrum of applications, ranging from elastomer and plastic cleaning, to cleaning-defluxing of electronic components and assemblies to precision-cleaning of any metal parts to heavy duty degreasing of metals, either in cold-immersion or vapor-degreasing processes. All members of this family are non-flammable, environmentally sound, user friendly and economical. Versatill® fluid replaces ANY non-flammable solvent in use today whether brominated, chlorinated or fluorinated solvents. Versatill® fluids outperforms most other non-flammable solvents while saving the user time and money.

Versatill® QP5 has azeotropic properties and is the basic member of the family upon which other members are built. Versatill® QP5 is an aggressive cleaner, aimed at degreasing and cleaning metal and ceramic surfaces from oils, greases and other soils. It can be utilized in existing vapor degreasing equipment after minimal adjustments. It is an excellent replacement option for solvents such as CFCs, PFCs, HFEs, HCFCs (HCFC-141b, HCFC-225) and aqueous cleaners, in terms of performance and cost.

Features

- Ideal for use in vapor degreasers and immersion cleaning. Can be accommodated in existing vapor degreasers.
- Outstanding performance with the highest solvency in its class and low surface tension
- Designed for cleaning heavy greases, oils, waxes, silicones and non-polar contaminants with high soils loading capacity
- Maintenance-free use in vapor degreaser, stable composition. No need for additives.
- Non-flammable and low in odor and toxicity for an excellent safety profile
- Environmentally sound - low global warming potential (GWP<32) and zero ozone depletion potential (ODP)
- Replacement for nPB, TCE, ozone-depleting HCFC and other expensive or high GWP HFC
- Faster cycle times, fast drying, lower energy usage.

Applications

- Cleaner-Degreaser of oil and grease.
- Vapor degreasing and cold cleaning.
- Defluxing printed circuit boards.
- Precision cleaning.
- Metal cleaning
- Carbon removal
- Silicone stripping
- Drying agent

Physical Properties

Table 1.

	Versatill® QP5	Novec™ 73DE	Opteon™ SE79	nPB	HCFC-141b	TCE	HCFC-225
Boiling Point °C (°F)	48 (119)	48 (119)	47 (117)	71 (160)	32 (90)	87 (188)	54 (129)
Liquid Density g/cm ³ (Kg./L)	1.29	1.28	1.29	1.35	1.24	1.44	1.55
Kauri Butanol Value	112	83	103	125	56	129	31
Viscosity, @25°C, cps	0.41	0.38	0.42	0.49	0.43	0.54	0.59
Surface Tension dyne/cm, @25°C	20	20	21	26	19	32	16
Vapor Pressure mmHg, @25°C	352	360	335	112	518	NA	216
Heat of Vaporization cal/gm	59.5	54.2	66.9	58.8	52.3	56.4	34.6
Flash Point, TCC	None	None	None	None	None	None	None
Flammability limits, v%	7-15	6-14.5	7.2-15.2	4-7.8	7.6-17.7	8.3-12.5	NA
ODP	0	0	0	0.01	0.1	0	0.03
GWP	23	47	15	0.3	782	0	400
PEL	200	200	200	10	500	10	50

Data compiled from publicly available sources. Not for specification purposes.

Conformity

Versatill® QP5 Designed Fluid conforms to the following specifications:

- **AMS1562B** Aircraft exterior surfaces (except for ASTM F484 Acrylic Stress Cracking)
- **ARP 1755B** Aircraft engine cleaning
- **ASTM-F-945** Stress corrosion of Titanium alloys (aircraft engine).
- **Boeing D6-17487P** Exterior and general cleaner.

Compatibility

Various plastics, elastomers and metals have been tested for compatibility with Versatill® QP5. Metals - in accordance with Mil-T-81533A, the metal corrosion test. Plastics and elastomers were tested for changes in weight, dimensions and appearance after immersion in boiling temperatures for 5 minutes followed by an hour drying.

Table 2.

Metal		Plastics		Elastomers	
Compatible	Incompatible	Compatible	Incompatible	Compatible	Incompatible
Aluminum		Acetal	ABS	PTFE	Silicone
Brass		Epoxy	Acrylic	Perfluoroelastomers	Fluorosilicone
Carbon steel		Nylon	Polycarbonate	Parfluor™	Buna N
Copper		PEEK	Styrene	Viton™ (perfluor)	Viton™ Non-fluor
Inconel		Polyester	PolySulfone	PTFE with EPDM	EPDM
Magnesium		Polyethylene			Butyl rubber
Monel		Polypropylene		PTFE with Neoprene	Neoprene
Stainless Steel		PTFE			
Titanium					

Safety

- Versatill® QP5 is not a reportable chemical under SARA 313.
- Versatill® QP5 is not regulated as a hazardous waste under RCRA.
- Versatill® QP5 is not regulated as a hazardous air pollutant under NESHAP.

For complete safety information, please refer to Versatill® QP5 Safety Data Sheet.

Packaging

Versatill® QP5 is available in 250 Kg. (551 Lb.) drums and 23 Kg. (50 Lb.) pails.

The product should be stored in the original containers in a cool, dry and ventilated place. Do not expose to temperatures higher than 120°F.

© 2019 Solvents Company, Inc. All rights reserved. The above information is furnished in good faith and believed to be accurate and reliable. Neither representations nor warranties are made, expressed or implied. User should make their own tests and determine suitability of the product to their needs. Nothing in here shall be construed as a permission for a use which might infringe upon a patent. Versatill® is a trademark licensed to Solvents Company, Inc.