



		Light Duty				Medium Duty			Heavy Duty								
Cleaning Degreasing		Versatill®				Versatill®			Versatill®			FLO™		Solvon®			
Properties	Unit	P	PE	L	LE	LC	LCa	SG35i	QP	QPi	SG65i	ZT	ZTe	PB	IP	AER	
Effectively Removes Soils	Fluoro Lubes	•	•	•	•	•	•										
	Particulates	•	•	•	•	•	•	•			•			•	•	•	
	Ionic Soils		•		•		•	•		•	•		•		•		
	Greases					•	•	•	•	•	•	•	•	•	•	•	
	Fluoro Greases	•	•	•	•	•	•	•			•						
	Silicones					•	•	•	•	•	•	•	•	•	•	•	
	Fluoro Silicones					•	•			•		•					
	Flux					•	•	•	•	•	•	•	•	•	•	•	
	Wax					•	•	•	•	•	•	•	•	•	•	•	
Solubility	Fluorocarbon	High	High	High	High	Mediu	Medium	Mediu	Low	Low	Low	Low	Low	Low	Low	Low	
	Hydrocarbon	Med.	Med.	Med.	Med.	High	High	High	High	High	High	High	High	High	High	High	
	Silicone	Low	Low	Low	Low	Med.	Med.	Med.	High	High	High	High	High	High	High	High	
Compatibility	<b>Plastics</b>	Requires Individual Testing				Requires Individual Testing			Requires Individual Testing					Requires Individual			
	Acrylics, ABS, Polycarbonate	High	High	High	High	None	None	None	None	None	None	None	None	None	None	None	
	PTFE, PEEK, Nylon, epoxy	High	High	High	High	High	High	High	High	High	High	High	High	High	High	High	
	<b>Silicon</b>	Med.	Med.	Med.	Med.	Low	Low	Med.	Low	Low	Low	Low	Low	Low	Low	Low	
	<b>Ceramics</b>	High	High	High	High	High	High	High	High	High	High	High	High	High	High	High	
	<b>Metals</b>	High	High	High	High	High	High	High	High	High	High	High	High	High	High	High	
Percision Cleaning Application	Co-Solvent	•	•	•	•												
	Vapor Degreasing	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	
	Immersion	•	•	•	•	•	•	•	•	•	•	•	•	•	•	•	
	Hand-Wipe	•	•	•	•	•	•	•	•	•	•	•	•				
	Spray Cleaning	•	•	•	•	•	•	•	•	•	•	•	•				

Not for specification purposes. All values @ 25°C unless otherwise specified.

Values gathered from public sources or calculated based on available

GWP-100 year ITH, CO<sub>2</sub> = 1.0

Trade marks are the property of their respective owners.